



RAJ CERAMICS

Z1 ACID PROOF BRICKS

Sl. No.	Brand	Water Absorption (%) max	Flexural Strength (Kg/cm ²) min	C.C.S. (Kg/cm ²) min	Resistance to acid (loss in wt.%) Max.	Remarks
1	RC AP I	2	100	700	1.5	Outsourced
2	RC AP II	4	70	500	4	Outsourced



1. The above values represent values obtained on standard squares in accordance with accepted test methods and are subject to manufacturing variations. This information is supplied as a technical service and may change without notice. Results are only indicative data and should not be used for specification/guarantee purposes. Size tolerance $\pm 1.5\%$ or $\pm 2\text{mm}$ whichever ever is greater.
2. We also make Bricks on tailor-made specification
3. Grading means 90% passing through the desired sieve

